

HANDLING SHEET

NatureWax™ Elite 300

HANDLING AND MELTING INSTRUCTIONS – TEXTURE SIDED PILLAR AND VOTIVE CANDLES

Step One: Melting of Wax – The wax should be heated to a temperature of 140° to 200°F (60.0 to 93.3°C) to melt the wax. Do not heat the wax above 200°F (93.3°C). If wax is held at higher temperatures for long periods of time it will discolor. Always use a thermometer when melting the wax and never leave your heated wax unattended. While the wax is melting stir the wax regularly to reduce localized heating of the wax. This will help to reduce burning of the wax while heating.

Step Two: Adding of Ingredients (other than Scent and Dye) – Other additives or ingredients may be added at any time to help improve the performance of the wax.

Step Three: Adding Candle Scent and Dye – The fragrances and dyes should be added to the wax after the wax is completely liquid. Make sure to stir the wax completely to ensure that the fragrances and dyes are completely mixed in.

Step four: Preparing the Wax for Pouring - After wax has been completely melted reduce the heat on the wax so that the wax cools to a temperature of 140 to 150°F (60.0 to 65.6°C). This will reduce discoloration of the wax after it has cooled.

Step Five: Pre-heating of Mold - The mold should not be heated. The mold should be at least 70 to 75°F (21.1 to 23.9°C), so that the wax will setup in the mold very fast creating the textured look in the wax. To really enhance the texturing the mold may be put into a refrigerator to get the mold cold. This will allow the wax to setup on the sides quickly.

Step Five: Pouring Candles – The wax should be poured into the mold while the wax is 140 to 150°F (60.0 to 65.6°C). If you do not get the look you want lower the temperature on the next candle. Remember that amount and type of fragrance can change the rate at which a wax will setup. Just as fragrance will affect the texturing of the candle so will the diameter of the candle. The larger the diameter of the candle the cooler the wax should be poured. If wax is to be left in melter over night the wax should be stored at a temperature of 140 to 150°F (60.0 to 65.6°C) to extend the life of the wax.

Step Six: Cooling of the candle – This wax can be cooled with and/or without the use of fans to increase the rate of cooling.

Step Seven: Relief hole – Relief holes are sometimes needed to help fill in voids that form in the middle of the candle. While this wax tends to not need this it is always good practice to do this to ensure that there are no problems while burning the candle. If a relief hole is needed, poke a hole in the middle of the top once there is a nice 1/8 in or more layer on the top. Let the candle sit for about 15 minutes and then pour wax into the hole to fill any voids in the wax. A thin layer of wax on the top of the candle is normal.

Step Eight: Curing of Candles – The candle should be allowed to cool and cure for at least 12 hours before the candle is burned. This will allow the crystals of the wax completely form giving a nice finish to the candle.

Disclaimer & Caution

Please refer to all relevant technical information specific to the product, prior to use. The information contained in this document is obtained from current and reliable sources. New Directions Aromatics Inc. provides the information contained herein, but makes no representation as to its comprehensiveness or accuracy. Individuals receiving this information must exercise their independent judgment in determining its appropriateness for a particular purpose. The user of the product is solely responsible for compliance with all laws and regulations applying to the use of the products, including intellectual property rights of third parties. As the ordinary or otherwise use(s) of this product is outside the control of New Directions Aromatics Inc., no representation or warranty, expressed or implied, is made as to the effect(s) of such use(s), (including damage or injury), or the results obtained. The liability of New Directions Aromatics Inc. is limited to the value of the goods and does not include any consequential loss. New Directions Aromatics Inc. shall not be liable for any errors or delays in the content, or for any actions taken in reliance thereon. New Directions Aromatics Inc. shall not be responsible for any damages resulting from use of or reliance upon this information. In the event of any dispute, the Customer hereby agrees that Jurisdiction is limited to the province of Ontario.

Notes:

- Maximum Recommended Fragrance – 5%
- Candles over 5 inches in diameter may need to be double wicked to ensure full melt pool.
- Works well with liquid or powdered dyes.

Disclaimer & Caution

Please refer to all relevant technical information specific to the product, prior to use. The information contained in this document is obtained from current and reliable sources. New Directions Aromatics Inc. provides the information contained herein, but makes no representation as to its comprehensiveness or accuracy. Individuals receiving this information must exercise their independent judgment in determining its appropriateness for a particular purpose. The user of the product is solely responsible for compliance with all laws and regulations applying to the use of the products, including intellectual property rights of third parties. As the ordinary or otherwise use(s) of this product is outside the control of New Directions Aromatics Inc., no representation or warranty, expressed or implied, is made as to the effect(s) of such use(s), (including damage or injury), or the results obtained. The liability of New Directions Aromatics Inc. is limited to the value of the goods and does not include any consequential loss. New Directions Aromatics Inc. shall not be liable for any errors or delays in the content, or for any actions taken in reliance thereon. New Directions Aromatics Inc. shall not be responsible for any damages resulting from use of or reliance upon this information. In the event of any dispute, the Customer hereby agrees that Jurisdiction is limited to the province of Ontario.